



Versatile Penetrating Masonry Sealer

For Professional Use Only

DESCRIPTION

- Water based pure, Acrylic non-yellowing penetrating Masonry Sealer
- May be used as Primer or Sealer
- Excellent penetration and adhesion to masonry surfaces.
- Rapid drying water-based technology.
- Compatible with most types of top coats
- Saves money by reducing absorption of top coats into substrate.
- Low VOC technology meets most VOC regulations.
- Primer for green Concrete/Stucco
- Easy to apply: Applies Milky, dries clear.

RECOMMENDED USES

Excellent sealer for vertical Masonry surfaces:

- Brick•Stucco•Concrete•EIFS•Tilt-Up•Split Block•Fluted Block•Concrete Block•Adobe•Masonite

Stabilizes chalky surfaces

Green Concrete/ Masonry Primer

Use as primer optimizes performance of any coating system.

Property	Result
Volume Solids	25% ± 2%
Weight Solids	27% ± 2%
Weight per Gallon	8.6 lbs per gallon ± 0.2
VOC	<100 g/liter
Clean Up	Water
Shelf Life-unopened	12 months @ 40-90°F
Viscosity	200 ± 100 cP

COLORS

Clear

PACKAGING/SHIPPING INFORMATION

CONTAINER SIZE	SHIPPING CLASS
55 Gallon drum (208.2 liters)	Class 55
5 Gallon pail (18.9 liters)	Class 55
2 Gallon pail (7.6 liters)	Class 55

SURFACE PREPARATION

Surface must be clean, dry and free of loose particles or other foreign matter.

APPLICATION

Product does not need dilution. This product may be brushed rolled or sprayed on a clean, dry surface. If material is sprayed it should be back rolled. For details see Equipment Recommendations at the end of this sheet.

Application Properties

Yield (1 gal to 150 sq ft)	5 dry mils
Dry Time (75° F)	2 to 3 hours
Recoat window	2 to 3 hours
Complete Cure	5 days

May be top-coated with Water Based or Oil based paints



Recommended Application Rates

Substrate*	First Coat (Gal/100sq.ft)	Final Coat (Gal/100sq.ft)
Brick	3/4	1/2
Stucco	1 1/4	3/4
Concrete	1	1/2
EIFS	1 1/4	3/4
Tilt-Up	0.5	1/3
Split Block	2.0	1.0
Fluted Block	2.0	1.0
Concrete Block	1 1/4	3/4
Adobe	1.0	0.5
Masonite	3/4	1/2
Chalky Surface	1/2	1/2

*Note: for green concrete or fresh stucco a minimum 10 day cure is required.

ENVIRONMENTAL CONDITIONS

This product cures by water evaporation only. Product must not be applied when the ambient temperature is below 50°F or if there is any possibility it could fall below 32°F within 24 hours of application. Application is not recommended if rain or dew is likely to occur before product dries. In high humidity conditions late afternoon applications should be avoided as overnight dew formation on uncured surface can cause coating wash-off. On marginal days, multiple applications of thin coats can ensure proper drying before rain or overnight freezes.

LIMITATIONS

Surface must be clean and dry
Do not apply when air or surface temperature is below 50°F or above 110°F. Surface temperature must be at least 5°F above the dew point. For optimum application properties, bring material to 60-80°F (16-27°C). Do not apply when inclement weather is imminent. Complete cure of Evercoat CS requires complete evaporation of water. Cool temperatures and high humidity retard cure.

Service temperatures must not exceed 180 degrees F.

To the best of our knowledge all technical data contained herein is true and accurate as of the date of issuance and subject to change without prior notice. Used must contact Everest systems Company to verify correctness before specifying or ordering. We guarantee our products to conform to the quality control standards established by Everest Systems Products. We assume no responsibility for coverage, performance or injuries resulting from use. Liability if any, is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY EVEREST SYSTEMS EXPRESSED OR IMPLIED; STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

SAFE PRACTICES

This product is designed for professional installation. Before working with this product, you must read and become familiar with the available information on its risks, proper use and handling. Information sources include but are not limited to SDS and product labels.

EQUIPMENT

Airless Spray: Minimum 1 gallon per minute pump; .011"-.013" tip; 1800-2400 psi; 1/4" high pressure material hose.

Conventional Spray: DeVilbiss MBC-510 gun; E tip; 704 Air Cap; 3/8" ID material hose; double regulated pressure tank with oil and moisture separator; 20 psi fluid pressure; 40-60 psi air pressure.

Brushes: Use nylon or polyester brushes.

Rollers: Use 1/2" to 3/4" synthetic roller covers.