

# NEOGARD

## 70620 ELASTOMERIC POLYURETHANE COATING

# PRODUCT DATA SHEET

### PRODUCT DESCRIPTION

70620 is a single component moisture-cured, aromatic, fire retardant, polyurethane coating designed for use as a base coat to protect polyurethane foam roofing systems.

### PRODUCT NUMBERS AND COLORS

Standard color is: Dark Gray

### CURED FILM PERFORMANCE

<u>Description</u>	<u>Test Method</u>	<u>Results</u>
Tensile Strength, min. PSI	ASTM D 412	1,000 PSI
Elongation at break, % at 75°F (23.9°C)	ASTM D 412	375%
Permanent Set at break	ASTM D 412	10%
Peel Adhesion to Foam	ASTM D 903 to Foam	20 lbf/in width
Moisture Vapor Trans. English Perms	ASTM E 96 Procedure B	5.0 perms @ 7.0 mils
Tear Resistance, Die C	ASTM D 1004	100 lbs/in
Hardness Shore A	ASTM D 2240	50-55
Resistance to Water % max. change in weight after 7 days immersion	ASTM D 471	3%

### PRODUCT DATA

<u>Description</u>	<u>Test Method</u>	<u>Results</u>
Viscosity, Krebs Unit	ASTM D 562	90-110
Weight - lbs./gal.	ASTM D 1475	11 lbs.
Weight Solids	ASTM D 1353	84.8%
Volume Solids	Calculated	76.9%
Flash Point	ASTM D 1310	113°F
Red Label		No
VOC -		1.68 lbs./gal.
Pot Life -		8 Hrs.
Shelf Life -		1 year
Cure Time @ 75°F, and 50% R.H.	TT-S-00230A	24 Hrs

### SAFETY

This product contains flammable aromatic solvents. Excessive contact with bare skin should be avoided. It is good practice to wear gloves and to guard against splashing the coating or solvent. Inhalation of fumes or vapor should be avoided. Use a NIOSH/MSHA approved respirator.

Thinning of materials is not required under normal application conditions. However, if required, thin material with Xylene. Never thin more than 10% without consulting Neogard. Xylene should be used for cleaning equipment.

For surface preparation and application instructions, refer to Neogard Guide Specifications.

### STORAGE

Every precaution should be taken to prevent fire. Drums and cans of coatings and solvents should be stored in a cool (75°F) area safe from fire exposure. When specified on container, protect materials from freezing. Open containers, the liquid coating, its fumes and vapor must be kept away from any source of ignition, heat, sparks, arcing switches, open flames, including pilot lights, cutting torches and all tools that could cause sparks. Do not smoke. Use explosion proof equipment. Foam or dry powder fire extinguishers should be placed where they can be quickly and safely reached in case of fire.

### FIRE RATINGS

70620 polyurethane coating was tested in a composite roofing system by Underwriters Laboratories, Inc. for the resistance of roof covering materials. For specific classifications, consult Underwriters Laboratories Building Materials Directory.

The information, data and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyer's process. **SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED** as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of any product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. The Licensed Neogard Applicator is an independent contractor of, and should under no circumstances be viewed as an employee or agent of, the Neogard Division of Jones-Blair. NTD111899db70620PD.p65

### NEOGARD

Div. of Jones-Blair

6900 Maple Avenue - P.O. Box 35288 - Dallas, Texas 75235 - Phone 214/353-1689 - Fax 214/357-7532