



VersaFlex Incorporated
686 S. Adams Street
Kansas City, KS 66105
913-321-9000
913-321-1490 (Fax)

Product Data Sheet

C-RUST™ Rust Converter

Product Description- *VersaFlex C-RUST* is a specially formulated, low solids, single component, rust converter. Its low viscosity contributes to ease of application on steel and other ferrous substrates.

Uses- *C-RUST* rust converter/primer may be used with all *VersaFlex* rapid curing polyurea sealants and spray coating systems. It is designed for use in both interior and exterior situations.

Chemical Composition- Water based active rust converter.

Physical Properties-

Color	White
Solids content, %	~40
Weight/gallon, lbs	8.6
Specific gravity @77°F	1.03
VOC, g/l	0
Odor	Slightly bitter
Dry to touch	30 minutes – 1 hour
Overcoat	24 – 72 hours
The value ranges stated in this Technical Data Sheet are based on system processing under laboratory conditions. Equipment configurations and/or field application conditions may produce variances in final system values.	

Packaging-

- One Gallon Kit: 1 gallon
- Five Gallon Kit: 5 gallons

Mixing- *C-RUST* is a single component product. Prior to use, shake container or stir for 1 to 2 minutes.

Application Recommendations- *C-RUST* should be applied by low-pressure sprayer, airless sprayer, roller or brush. Apply at 300 – 400 square feet per gallon depending on surface condition. Ferrous substrates must be clean, dry and sound prior to installation of *C-RUST*. Wait a minimum of 12 hours to overcoat with polyurea or other *VersaFlex* products. Dried *c-RUST* will turn a black color, designating it ready to be overcoated. Not to be used for immersion applications.

Safety- Review MSDS at *VersaFlex.com*

Basic safety for personal protection is:

- Long sleeve overalls or disposable Tyvex overalls
- Rubber gloves
- Splash shield or safety glasses with splash guards
- Rubber or leather boots
- Respirator
- Do not use near high heat or open flame
- Do not take internally
- Keep out of reach of children

Shelf Life- One year from date of shipment, in original, unopened factory containers, under normal storage conditions of 55°F to 95°F (18°-35°C).

Technical Services- Sales and Customer Support 913-321-9000

Warranty- *VersaFlex Incorporated* will refund the price of or replace, at its election, product it finds to be defective provided the product has been used properly. Except as expressly stated above, the company makes no warranty of merchantability and no warranty of fitness for any particular purpose, nor does it make any warranty, expressed or implied, of any nature whatsoever with respect to the product of its use. In no event shall the company be liable for delay caused by defects, for loss of use, for indirect, special or consequential damages, or for any changes or expenses of any nature incurred without its written consent.